

MetaGuard Crystal Laminate

Textured 'Anti-Scuff' Lustre Laminate



Product Description

MetaGuard Crystal Laminate is a 100 micron textured overlamine ideal for indoor point of sale, exhibition graphics and posters. The sandtex lustre finish minimalises glare and offers excellent anti-scuff properties. Suitable for overlaminating solvent, eco-solvent and latex prints.

Features and Benefits

- Matched to Metamark Monomeric Print films.
- 100 micron textured film.
- Textured anti-scuff finish.
- SandTex lustre film minimalises glare.

Face Film

Face Film	Monomeric Calendered PVC
Gauge (ISO 2286-3)	100 micron nominal
Tensile strength	65N/25mm MD / 57N/25mm TD norm

Adhesive

Type	Permanent Solvent-Free Acrylic
Adhesion to glass 20 mins	13N/25mm nominal
Adhesion to glass 24 hour	20N/25mm nominal
Application temperature	+10°C to +40°C
Service temperature	-30°C to +100°C

Release Liner

Print	Plain
Weight	140 gsm nominal
Type	Kraft

Finishes

Finishes Available	MG-CL	Crystal Laminate
--------------------	-------	------------------

Roll Presentation

Roll Widths	1.37m / 1.52m
Roll Lengths	50m

Durability

Shelf Life	1 years. (10-20°C and 50% R.H).
Durability	3 years
Fire Rating	Self-extinguishing.
Chemical Resistance	Unprinted film resistant to mild acids, aliphatic solvents, salt and alkali, diesel, gasoline, paraffin, hydraulic oil, antifreeze.

Handling and Application

- This product is suitable for cold lamination using a laminator.
- Ensure that the material has reached room temperature and a relative humidity of 50% before printing.
- Do not handle the face film, ensure free from dust and static.
- Allow the inks to cure before overlaminating, this is usually 24-48 hours. (Not applicable to HP Latex prints)
- Suitable for use on solvent, eco-solvent and latex prints.
- Apply around 30°C on the top roller to prevent silvering of the adhesive.
- Refer to www.metamark.co.uk for further application guidelines.
- The user should determine suitability of the overlamine to the print media.

MetaSure® Warranty

Metamark (UK) Limited warrants to its customers that graphics produced using Metamark Media and Overlaminates will remain in good condition without excessive fading or colour degradation for the specified life time of the ink used, when correctly stored, printed and applied in accordance with procedures outlined in the technical literature. If within the specified years of normal use Metamark Media and Overlaminates becomes ineffective for its intended use, then Metamark will provide sufficient material to produce a new replacement marking, and will at its own discretion, contribute an allowance in additional material towards the costs involved in replacing the graphics. In all cases, the converter is held fully responsible for storing, processing and applying the unconverted materials in accordance with Metamark's technical specifications. Metamark (UK) Limited will not be liable for any indirect or consequential loss or damage, and will not provide any allowance against improper usage, application accident, negligence, chemical damage or improper repair. The above data is given in good faith to provide an indication of the performance of the product. Purchasers should consider the suitability of each product for its intended use and the purchaser assumes all risks in connection with such use. Seller shall not be liable for damages in excess of the purchase price of the product nor for incidental nor consequential loss.

Metamark (UK) Limited

☐ Lunsdale • New Quay Road • Lancaster • LA1 5QP • Tel +44 (0)1524 387140

☐ Metamark House • Genesis Business Park • Albert Drive • Woking • GU21 5RW • Tel +44 (0)1483 571111

sales@metamark.co.uk
www.metamark.co.uk