

MetaGuard UV

PVC Overlaminates for UV Prints



Product Description

MetaGuard UV Overlaminates has been developed for the finishing and protection of UV Prints. The specially formulated solvent based adhesive gives a high bond to the low energy surface of UV prints and overcomes silvering. Available in a Matt or Gloss finish, it offers a very high level of clarity and definition to the print. The 70 micron film gives a high level of abrasion resistance, and can be used on flat or simple curves. Fire Rating Class B [BS EN 13501-1:2007].

Features & Benefits

- UK Manufactured.
- Matched to Metamark MD3 Print films.
- MetaSure Warranty with 5 year durability.
- For use on Solvent, Eco Solvent, Latex and UV prints.

Face Film		Finishes		
Face Film	Polymeric calendered PVC	Finishes Available	MG-UV-105	Gloss
Gauge (ISO 2286-3)	70 micron nominal		MG-UV-102	Matt
Tensile Strength	47N/25mm MD / 43N/25mm TD nom	Roll Presentation		
Elongation at break	180% MD nominal	Roll Widths	1.37m / 1.60m	
Adhesive		Roll Lengths	50m	
Type	Permanent clear pressure sensitive solvent-based acrylic with UV inhibitors	Durability		
Adhesion to glass 20 mins	17N/25mm nominal	Shelf Life	1 years. (10-20°C and 50% R.H).	
Adhesion to glass 24 hour	23N/25mm nominal	External weathering	5 years (Unprinted). Northern European conditions, vertical. Refer to full Metamark International durability guide.	
Application temperature	+10°C to +60°C	Fire Rating	Class B - BS EN 13501-1:2007	
Service temperature	-30°C to +110°C	Chemical Resistance	The unprinted film is resistant to mineral oils, fats and fuels, aliphatic solvents, mild acids, salt and alkali for e.g. diesel oil gasoline, paraffin, hydraulic oil, ant-freeze, soap suds, etc.	
Release Liner		Regulations	REACH and RoHS Compliant.	
Print	'Metamark Digital Vinyl' Grey print			
Weight	140 gsm nominal			
Type	Solventless Kraft			

Handling and Application

- This product is suitable for cold lamination using a laminator.
- Ensure that the material has reached room temperature and a relative humidity of 50% before printing.
- Do not handle the face film, ensure free from dust and static.
- Allow the inks to cure before overlaminating, this is usually 24-48 hours (darker colours can be longer).
- Suitable for use on Eco Solvent, Solvent, Latex & UV prints.
- The product is matched to MD3. Matched laminates prevent tunnelling and delamination.
- Apply around 30°C on the top roller to prevent silvering of the adhesive.
- The user should determine suitability of the overlaminates to the print media.

MetaSure® Warranty

Metamark (UK) Limited warrants to its customers that graphics produced using Metamark Media and Overlaminates will remain in good condition without excessive fading or colour degradation for the specified life time of the ink used, when correctly stored, printed and applied in accordance with procedures outlined in the technical literature. If within the specified years of normal use Metamark Media and Overlaminates becomes ineffective for its intended use, then Metamark will provide sufficient material to produce a new replacement marking, and will at its own discretion, contribute an allowance in additional material towards the costs involved in replacing the graphics. In all cases, the converter is held fully responsible for storing, processing and applying the unconverted materials in accordance with Metamark's technical specifications. Metamark (UK) Limited will not be liable for any indirect or consequential loss or damage, and will not provide any allowance against improper usage, application accident, negligence, chemical damage or improper repair. The above data is given in good faith to provide an indication of the performance of the product. Purchasers should consider the suitability of each product for its intended use and the purchaser assumes all risks in connection with such use. Seller shall not be liable for damages in excess of the purchase price of the product nor for incidental nor consequential loss.

Metamark (UK) Limited

- Lunsdale • New Quay Road • Lancaster • LA1 5QP • Tel +44 (0)1524 387132
- Metamark House • Genesis Business Park • Albert Drive • Woking • GU21 5RW • Tel +44 (0)1483 571111

sales@metamark.co.uk
www.metamark.co.uk