# Metamark MM-CCG Colour Change

## Cylinder Cast Wrapping Film with MetaGlide



## **Product Description**

Metamark Colour Change, featuring MetaGlide adhesive technology, is a professional wrap film for vehicle personalisation, for use on fleet, commercial and taxi applications. The next generation micro-channel air release system gives optimal performance with enhanced repositionability, and high adhesive strength. This gives total confidence when fitting into 3D channels and recesses. Metamark MM-CCG Colour Change film can be removed cleanly at the end of the desired application and provides the added benefit of protection to the factory paint during use. The product is warranted for up to 8 years with the MetaSure warranty.

#### **Features & Benefits**

- Cylindered Cast 100 micron Film for full vehicle wraps.
- Repositionable, layflat stability, and smooth release handling.
- MetaGlide micro channel adhesive offers enhanced handling.
- Available to colour match (Minimum quantity applies).
- Engineered to give long term dimensional stability.
  - Up to 8 year durability.

Face Film		Finishes	
Face Film	Cylinder Cast Vinyl	Finishes Available	Please contact us for more details.
Gauge	100 micron nominal	Roll Presentation	
Adhesive		Roll Sizes & Net Weight	1520mm x 50m 22kg
Гуре	MetaGlide Micro Channel Solvent-Based Adhesive.	Presentation	Face film outwards, on a 76mm core.
Adhesion to glass 20 mins	ass 20 mins 11N/25mm nominal ass 24 hour 18N/25mm nominal Medium Medium to High nperature +10°C to +50°C	Durability	
Adhesion to glass 24 hour Perceived Tack Shear Strength Application temperature Service temperature		Shelf Life External weathering	2 years. (10-20°C and 50% R.H). 8 years for black and white, 7 years fo colours and 5 years for metallic ; in vertical exposure under northern European conditions.
Release Liner		Fire Rating Dimensional Stability	Self-extinguishing. <0.5% (48h at 70°C on aluminium)
Print Weight Type	'MetaGlide' print 140 gsm nominal Structured micro channel PE layflat	Regulations Chemical Resistance	REACH compliant Resistant to mineral oils, fats and fuels, aliphatic solvents, mild acids, sal and alkali for e.g. diesel oil, gasoline, paraffin, hydraulic oil, antifreeze, soap suds etc.

#### Application

- Refer to 'MM-CC' application guidelines to ensure correct installation.
- Use a dry application method.
- Use gentle heat to allow conformability.
- Do not overstretch as this will cause the application to fail.
- After application 'superheat' the film into recesses at 100-105°C.
- Metallic and Matt versions should be applied in the same direction.
- Yellow and Tangerine are not suitable for use on darker vehicles due to low opacity.
- Suitable for plotter use also for contour and vinyl lettering.
- It is advised to contact insurers when changing the colour of the vehicle.
- The user should determine suitability for the vehicle.

#### MetaSure® Warranty

Metamark (UK) Limited warrants to its customers that completed decorative markings which utilise Metamark SignVinyl will remain in good condition without excessive fading or colour degradation for the specified life time of each material when correctly stored and applied in accordance with procedures outlined in the technical literature. If within the specified years of normal use Metamark SignVinyl becomes ineffective for its intended use, then Metamark will provide sufficient material to produce a new replacement marking, and will also, at its own discretion, contribute an allowance towards the costs involved in replacing the graphics. Please Note: The above data is given in good faith to provide an indication of the performance of the product. Purchasers should consider the suitability of each product for its intended use and the purchaser assumes all risks in connection with such use. Seller shall not be liable for damages in excess of the purchase price of the product nor for incidental nor consequential loss.

### Metamark (UK) Limited