# Metamark M-PPF<sup>®</sup> R

# Self-Healing 5 year TPU Paint Protection Film



## **Product Description**

Metamark M-PPF<sup>®</sup> Paint Protection Films use advanced TPU film technologies to ensure the highest level of performance. The product offers high levels of protection to the factory paint finish, giving resistance to contaminants, abrasion, scratches, stone chips, bird soiling, and daily wear. The optically clear high gloss film of M-PPF<sup>®</sup> R has a self-healing top-coat. M-PPF<sup>®</sup> films can be cleanly removed. The conformable film can be used as a full or partial wraps. The product is protected by a cap sheet which should be removed before application. Metamark M-PPF<sup>®</sup> R is covered by a 5 year MetaSure warranty.

### **Features & Benefits**

- Polycaprolactone based, aliphatic TPU film.
- Good protection against scratches and stone chips.
- PVC, Phthalate and Chlorine Free.
- Supplied with added PET cap sheet.
- 5 year durability and MetaSure Warranty\*

Face Film		Finishes	
Face Film Cap Sheet Gloss Value	165 micron 50 micron > 80% (60° angle of incidence) 550% (D-412)	Finishes Available	M-PPF R Clear High Gloss
		<b>Roll Presentation</b>	
Elongation at break		Roll Widths	1.52m
Adhesive		Roll Lengths	15m
Туре	Repositionable and removable acrylic	Durability	
Application temperature	+5°C to +30°C -30°C to +110°C	Shelf Life	2 years. (10-20°C and 50% R.H).
Service temperature		External weathering	5 years. Northern European conditions, vertical. Refer to full Metamark
Release Liner			International durability guide.
Туре	PET	*Warranty	Excludes yellowing

#### MetaSure® Warranty

Metamark (UK) Limited warrants to its customers that Metamark films are manufactured to specification and free of material defects. If the films prove defective then Metamark will replace the material, and will at its own discretion, contribute an allowance in additional material towards the costs involved in replacing the product. In all cases, the converter is held fully responsible for storing, processing, and applying the unconverted materials in accordance with Metamark's technical specifications. Metamark (UK) Limited will not be liable for any indirect or consequential loss or damage, and will not provide any allowance against improper usage, application accident, negligence, chemical damage, or improper repair. The above data is given in good faith to provide an indication of the performance of the product. Purchasers should consider the suitability of each product for its intended use and the purchaser assumes all risks in connection with such use. Seller shall not be liable for damages in excess of the purchase price of the product nor for incidental nor consequential loss.