MetaGuard UV

PVC Overlaminate for UV Prints



Product Description

MetaGuard UV Overlaminate has been developed for the finishing and protection of UV Prints. The specially formulated solvent based adhesive gives a high bond to the low energy surface of UV prints and overcomes silvering. Available in a Matt or Gloss finish, it offers a very high level of clarity and definition to the print. The 70 micron film gives a high level of abrasion resistance, and can be used on flat or simple curves. Fire Rating Class B [BS EN 13501-1:2007].

Features & Benefits

- UK Manufactured.
- Matched to Metamark MD3 Print films.

- MetaSure Warranty with 5 year durability.
- For use on Solvent, Eco Solvent, Latex and UV prints.

Face Film		Finishes	
Face Film Gauge (ISO 2286-3) Tensile Strength	Calendered PVC 70 micron nominal 50N/25mm MD / 48N/25mm TD	Finishes Available	MG-UV-105 Gloss MG-UV-102 Matt
Elongation at break	180% MD nominal	Roll Presentation	
Adhesive		Roll Widths Roll Lengths	1.37m / 1.60m 50m
Туре	Permanent clear solvent-based acrylic with UV inhibitors	Durability	
Adhesion to glass 20 mins Adhesion to glass 24 hour Application temperature Service temperature	17N/25mm nominal 23N/25mm nominal +10°C to +50°C -30°C to +100°C	Shelf Life External weathering	1 years. (10-20°C and 50% R.H). 5 years (Unprinted). Northern European conditions, vertical. Refer to full Metamark International durability guide.
Release Liner		Fire Rating	Class B - BS EN 13501-1:2007. The full classification is 'B / s2 / d0'.
Print Weight Type	'Metamark Digital Vinyl' Grey print 140 gsm nominal Kraft	Chemical Resistance	The unprinted film is resistant to mineral oils, fats and fuels, aliphatic solvents, mild acids, salt and alkali for e.g. diesel oi gasoline, paraffin, hydraulic oil, ant-freeze, soap suds, etc.
		Regulations	REACH and RoHS Compliant.

Handling and Application

- This product is suitable for cold lamination using a laminator.
- Ensure that the material has reached room temperature and a relative humidity of 50% before printing.
- Do not handle the face film, ensure free from dust and static.
- Allow the inks to cure before overlaminating, this is usually 24-48 hours (darker colours can be longer).
- Suitable for use on Eco Solvent, Solvent, Latex & UV prints.
- The product is matched to MD3. Matched laminates prevent tunnelling and delamination.
- Apply around 30°C on the top roller to prevent silvering of the adhesive.
- The user should determine suitability of the overlaminate to the print media.

MetaSure® Warranty

Metamark (UK) Limited warrants to its customers that graphics produced using Metamark Media and Overlaminates will remain in good condition without excessive fading or colour degradation for the specified life time of the ink used, when correctly stored, printed and applied in accordance with procedures outlined in the technical literature. If within the specified years of normal use Metamark Media and Overlaminates becomes ineffective for its intended use, then Metamark will provide sufficient material to produce a new replacement marking, and will at its own discretion, contribute an allowance in additional material towards the costs involved in replacing the graphics. In all cases, the converter is held fully responsible for storing, processing and applying the unconverted materials in accordance with Metamark's technical specifications. Metamark (UK) Limited will not be liable for any indirect or consequential loss or damage, and will not provide any allowance against improper usage, application accident, negligence, chemical damage or improper repair. The above data is given in good faith to provide an indication of the performance of the product. Purchasers should consider the suitability of each product for its intended use and the purchaser assumes all risks in connection with such use. Seller shall not be liable for damages in excess of the purchase price of the product nor for incidental nor consequential loss.

Metamark (UK) Limited