

MetaGuard UV

PVC Overlamine for UV Prints



Product Description

MetaGuard UV Overlamine has been developed for the finishing and protection of UV Prints. The specially formulated solvent based adhesive gives a high bond to the low energy surface of UV prints and overcomes silvering. Available in a Matt or Gloss finish, it offers a very high level of clarity and definition to the print. The 70 micron film gives a high level of abrasion resistance, and can be used on flat or simple curves. Fire Rating Class B [BS EN 13501-1:2007].

Material Handling

- This product is suitable for cold lamination using a laminator. Apply around 30°C on the top roller to prevent silvering of the adhesive.
- Ensure that the material has reached room temperature and a relative humidity of 50% before use.

Overlaminating

- Suitable for prints with UV cured Ink technology, as well as Solvent, Eco Solvent inkjet and Latex inks.
- The product is matched to Metamark media. The user should determine suitability of the overlamine to other print media.
- Allow the inks to cure before overlaminating. Failure to do so can cause delamination, tunnelling and shrinkage.
- Refer to www.metamark.co.uk for further application guidelines.
- The user should determine suitability of the overlamine to the print media.

Face Film

Face Film	Calendered PVC
Gauge	70 micron nominal
Tensile Strength	50N/25mm MD / 48N/25mm TD
Elongation at break	180% MD nominal

Adhesive

Type	Permanent clear solvent-based acrylic with UV inhibitors
Weight	23gsm nominal
Adhesion to glass 20 mins	17N/25mm nominal
Adhesion to glass 24 hour	23N/25mm nominal
Perceived tack	High
Application temperature	+5°C to +60°C
Service temperature	-30°C to +110°C

Release Liner

Print	'Metamark Digital Vinyl' blue print
Weight	140 gsm nominal
Type	Kraft

Finishes

Finish Available	MG-UV-102	Matt
	MG-UV-105	Gloss

Roll Presentation

Roll sizes and net weights	1370mm x 50m	20kg
	1600mm x 50m	23kg

Presentation	Laminate outwards, on a 76mm core.
--------------	------------------------------------

Durability

Shelf Life	1 year
External weathering	5 years. This refers to the overlamine and not the protection that it gives the printed image.
Fire Rating	Class B - BS EN 13501-1:2007. The full classification is 'B / s2 / d0'.
Dimensional Stability	<0.4mm (48h at 70°C on aluminium)
Chemical Resistance	Resistant to mineral oils, fats and fuels, aliphatic solvents, mild acids, salt and alkali, diesel oil, gasoline, paraffin, hydraulic oil, antifreeze, soap suds, etc.
Regulations	REACH and RoHS compliant

Warranty: Metamark (UK) Limited warrants to its customers that graphics produced using Metamark Digital Media will remain in good condition without excessive fading or colour degradation for the specified life time of the ink used, when correctly stored, printed and applied in accordance with procedures outlined in the technical literature. If within the specified years of normal use Metamark DigitalVinyl becomes ineffective for its intended use, then Metamark will provide sufficient material to produce a new replacement marking, and will at its own discretion, contribute an allowance in additional material towards the costs involved in replacing the graphics. In all cases, the converter is held fully responsible for storing, processing and applying the unconverted materials in accordance with Metamark's technical specifications. Metamark (UK) Limited will not be liable for any indirect or consequential loss or damage, and will not provide any allowance against improper usage, application accident, negligence, chemical damage or improper repair. **Please Note:** The above data is given in good faith to provide an indication of the performance of the product. Purchasers should consider the suitability of each product for its intended use and the purchaser assumes all risks in connection with such use. Seller shall not be liable for damages in excess of the purchase price of the product nor for incidental nor consequential loss.

Metamark (UK) Limited

○ Luneside • New Quay Road • Lancaster • LA1 5QP • Tel +44 (0)1524 387140 • Fax +44 (0)1524 387147

○ Metamark House • Octimum Business Park • Forsyth Road • Woking • GU21 5SF • Tel +44 (0)1483 571111 • Fax +44 (0)1483 570540

sales@metamark.co.uk

www.metamark.co.uk