





# AURORA®

## SPECIFICATIONS

Composition	Average Thickness	Carrier	Certifications
PU	200 microns	adhesive Polyester	<p>REACH n° 1907/2006/EU</p>   <p>23.HIT.76049 Hohenstein HTTI</p>  

## APPLICATION INSTRUCTIONS

APPLIES ON	SUGGESTED CUTTING SETTINGS			TRANSFER SETTINGS			
cotton, polyester, poly/cotton blends (not suited for treated and dye sublimated textiles)	Blade	Pressure	Speed	Time	Temperature	Pressure	Peel
	60°	100 gf	25 cm/sec	15 seconds	150°C (302°F)	medium (3 bar)	cold

- Mirror cut the design
- Weed excess material
- Place the design on the garment
- Heat apply at the conditions shown above
- Peel carrier cold

### PRODUCT HIGHLIGHTS

- Shimmering look, with glossy finish
- Iridescent colors
- Structured surface



**NOTE: We highly recommend to perform a test, before launching a production!**

## CARE AND WASHING RECOMMENDATIONS

Washing	Ironing	Tumble dry	Dry cleaning	Storage Shelf Life	Storage Temperature	Storage Conditions	Position
Up to 60°C, best inside-out	YES best inside - out	YES (synthetic cycle)	NO	Up to 2 years	Between 18°C and 26°C	Away from sunlight and dust	Vertical

- Wait 24 hours after the application before the first wash
- Respect the textile recommendations
- Do not bleach or use aggressive chemical agents