

BRICK® 600

SPECIFICATIONS

Composition	्रं Average Thickness	Carrier	Certifications		
PU	600 microns	Non adhesive Polyester	OEKO TEX® REACH n° 1907/2006 STANDARD 15.HIT.78859 Hohenstein HTII 100 HOHENSTEIN HTI)/EU	



Z

APPLICATION INSTRUCTIONS | Laser friendly



⊘ APPLIES ON	SUGGESTED CUTTING SETTINGS			TRANSFER SETTINGS			
cotton, polyester, poly/cotton blends (not suited for treated	▲ Blade	≟ Pressure	>> Speed	Time	Temperature	Pressure	Peel
and dye sublimated textiles)	60°	80 gf	10 cm/sec	25 seconds	155°C (311°F)	medium/high (4 bar)	cold

NOTE: Due to the thickness of the material, we do not recommend cutting details of dimensions less than 0,5 cm

- → Mirror cut the design
- → Weed excess material
- → Preheat the garment for 20 seconds
- \rightarrow Place the design on the garment
- \rightarrow Heat apply at the conditions shown above
- → Peel carrier cold

PRODUCT HIGHLIGHTS

- → Matt finish
- → Thickness adds dimension to any logo
- → Soft to the touch



NOTE: We highly recommend to perform a test, before launching a production!

CARE AND WASHING RECOMMENDATIONS

Washing	# Ironing	⊡ Tumble dry	Ony cleaning	Storage Shelf Life	Storage Temperature	Storage Conditions	∮ Position
Up to 40°C, best inside-out	YES best inside- out	YES (cotton cycle)	NO	Up to 2 years	Between 18°C and 26°C	Away from sunlight and dust	Vertical

- ightarrow Wait 24 hours after the application before the first wash
- → Respect the textile recommendations
- → Do not bleach or use aggressive chemical agents