












EASY REFLECTIVE®

SPECIFICATIONS

Composition	Average Thickness	Carrier	Certifications
PU + glass pearls	150-170 microns	Adhesive polyester	<div>   </div> <div> REACH n° 1907/2006/EU Silver only: EN 20471 </div> <div>   </div>

APPLICATION INSTRUCTIONS

Applies on	SUGGESTED CUTTING SETTINGS			TRANSFER SETTINGS			
cotton, polyester, poly/cotton blends, spandex, Nylon, treated fabrics, leather - (not suited for dye sublimated textiles)							
	Blade	Pressure	Speed	Time	Temperature	Pressure	Peel
	45°	90-130gf	15 cm/sec	15 seconds	150°C (302°F)	Medium (2,5/3,5 bar)	hot









- Mirror cut the design Weed excess material
- Place the design on the garment
- Heat apply at the conditions shown above
- Remove the carrier in warm conditions

PRODUCT HIGHLIGHTS

- High retroreflectivity power
- Adhesive carrier helps cutting small details
- Silver color follows EN ISO 20471 regulation
- Also suitable for "difficult textiles" (Nylon, treaded garments)

 **NOTE:** We highly recommend to perform a test before launching a production

CARE AND WASHING RECOMMENDATIONS

 Washing	 Ironing	 Tumble dry	 Dry cleaning	 Storage Shelf Life	 Storage Temperature	 Storage Conditions	 Position
Up to 40°C, best inside-out	YES best inside-out	YES (synthetic cycle)	NO	Up to 2 years	Between 18°C and 26°C	Away from sunlight and dust	Vertical

- Wait 24 hours after the application before the first wash
- Respect the textile recommendations
- Do not bleach or use aggressive chemical agents