

STRIPFLOCK PRO™

SPECIFICATIONS

	 Composition	 Average Thickness	 Carrier	 Oeko-Tex	 Certifications
Stripflock™ Pro standard colors*	PVC	650 microns	Adhesive Polyester	class I	 
Stripflock™ Pro fluo colors	PU	620 microns		class II	  

*Stripflock Pro black Oeko-Tex standard 100 class II

APPLICATION INSTRUCTIONS

 Applies on	SUGGESTED CUTTING SETTINGS			TRANSFER SETTINGS			
cotton, polyester, poly/cotton blends (not suited for treated and dye sublimated textiles)	 Blade	 Pressure	 Speed	 Time	 Temperature	 Pressure	 Peel
	60°	60 gf	15 cm/sec	15 seconds	155°C (311°F)	Medium (2,5/3,5 bar)	warm

- Mirror cut the design
- Weed excess material
- Place the design on the garment
- Heat apply at the conditions shown above
- Peel carrier warm

PRODUCT HIGHLIGHTS

- velvet touch
- embroidery look

 **NOTE:** Stripflock Pro cannot be layered on itself. We highly recommend to perform a test before launching a production.

CARE AND WASHING RECOMMENDATIONS

 Washing	 Ironing	 Tumble dry	 Dry cleaning	 Storage Shelf Life	 Storage Temperature	 Storage Conditions	 Position
Up to 60°C, inside-out	YES inside-out	YES (cotton cycle)	NO	Up to 2 years	Between 18°C and 26°C	Away from sunlight and dust	Vertical

- Wait 24 hours after the application before the first wash
- Respect the textile recommendations
- Do not bleach or use aggressive chemical agents