Metamark MD5-AB

High Performance Digital Vinyl with Grey MetaScape® Adhesive



White Gloss

Product Description

Metamark MD5A-B features the MetaScape® adhesive system, offering faster and easier application by providing air with an exit route from under the graphic, with greater repositioning during application. This is combined with a grey pigmented solvent-based adhesive to provide increased opacity and preventing the substrate colour showing through. Metamark's high performance 70 micron white face film with its distinctive coating technology produces outstanding print performance on Solvent, Eco Solvent, UV and Latex printers. UK Manufactured.

Features & Benefits

- Carbon Neutral Product¹.
- For Solvent, Eco Solvent, Latex and UV printing.
- MetaScape® Adhesive System allowing ease of application.
- 7 year durability and MetaSure Warranty.

MetaStream Ready[™].

Finishes

Roll Widths

Roll Lengths

Druability

Shelf Life

Fire Rating

Finishes Available

Roll Presentation

External weathering

- Printer manufacturer specified reference media.
- MD Series for best in class print quality & wide colour gamut.

MD5-AB

50m / 25m

0.76m / 1.37m / 1.60m

2 years. (10-20°C and 50% R.H).

Class B - BS EN 13501-1:2018

7 years (unprinted). Northern European conditions, vertical. Refer to full

Metamark International durability guide.

- Engineered to give long term dimensional stability.
- ¹ This product has been carbon offset from cradle to first customer plus end of life. See website for details.

Face Film

Face Film Gauge (ISO 2286-3) **Tensile Strength** Elongation at break Polymeric Calendered Vinyl 70 micron nominal 47N/25mm MD / 43N/25mm TD nom. 180% MD nominal

Adhesive

Туре	MetaScape [®] permanent grey solvent
	based acrylic with air channels.
Adhesion to glass 20 mins	15N/25mm nominal
Adhesion to glass 24 hour	20N/25mm nominal
Application temperature	+10°C to +60°C
Service temperature	-30°C to +110°C

Release Liner

Print	MetaScape [®] print
Weight	140 gsm nominal
Туре	Structured Layflat kraft paper with PE
	coating

Printing and Handling

- Always perform a test print first. Ensure that the correct profiles and heater settings are used. Refer to www.metamark.co.uk.
- Ensure that the material has reached room temperature and a relative humidity of 50% before printing.
- Do not handle the face film, ensure free from dust and static.
- Overlamination is recommended to prevent abrasion, extends colour fastness, and also offers easier handling.
- The matched laminate for MD5-AB is MetaGuard MG-700 Series.









MetaSure® Warranty

Metamark (UK) Limited warrants to its customers that graphics produced using Metamark Media and Overlaminates will remain in good condition without excessive fading or colour degradation for the specified life time of the ink used, when correctly stored, printed and applied in accordance with procedures outlined in the technical literature. If within the specified years of normal use Metamark Media and Overlaminates becomes ineffective for its intended use, then Metamark will provide sufficient material to produce a new replacement marking, and will at its own discretion, contribute an allowance in additional material towards the costs involved in replacing the graphics. In all cases, the converter is held fully responsible for storing, processing and applying the unconverted materials in accordance with Metamark's technical specifications. Metamark (UK) Limited will not be liable for any indirect or consequential loss or damage, and will not provide any allowance against improper usage, application accident, negligence, chemical damage or improper repair. The above data is given in good faith to provide an indication of the performance of the product. Purchasers should consider the suitability of each product for its intended use and the purchaser assumes all risks in connection with such use. Seller shall not be liable for damages in excess of the purchase price of the product nor for incidental nor consequential loss.

Metamark (UK) Limited

☐ Luneside • New Quay Road • Lancaster • LA1 5QP • Tel +44 (0)1524 387140

D Metamark House • Genesis Business Park • Albert Drive • Woking • GU21 5RW • Tel +44 (0)1483 571111

sales@metamark.co.uk www.metamark.co.uk

- **Dimensional Stability** <0.3mm (48h at 70°C on aluminium) **Chemical Resistance** Unprinted film resistant to mild acids, aliphatic solvents, salt and alkali, diesel, gasoline, paraffin, hydraulic oil, antifreeze. Regulations **REACH and RoHS Compliant.** Application Allow a minimum of 24-48 hours for the solvents to dry off before application of the overlaminate, or to the substrate, depending on
 - the print and drying conditions this can often be in excess of 48 hours. Retained solvents will reduce adhesion levels. Not recommended for use on low energy surfaces such as
- polypropylene.
- Apply unstressed, in particular to curves and recesses. It is not suitable for application over rivets or complex recesses.
- Suitable for dry application only.
- The user should determine suitability of substrate.